



PRI Construction Materials Technologies LLC

6412 Badger Drive

Tampa, FL 33610

813.621.5777

<https://www.pri-group.com/>

Laboratory Test Report

Report for: Aida Ricetti
Hardscape.com
15132 Park of Commerce Blvd. Ste # 103
Jupiter, FL 33487

Product Name(s): Calacata
Project No.: 2275T0003.12
Dates Tested: Sep. 14, 2021
Test Methods: ASTM C1371
ASTM C1549
ASTM E1980

Results Summary:

<u>Product</u>	<u>SRI, Medium-Wind</u>
Calacata	69

Purpose: Determine the solar reflectance, thermal emittance, and solar reflectance index value(s) of the tested product(s).

Test Methods: The test methods used included ASTM C1549-16: *Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using a Portable Reflectometer*, Procedure B and ASTM C1371-15: *Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emissometers*. Thermal emittance measurement for samples was modified in accordance with Devices and Services Company's Tech Note 04-1. Both of these methods are Energy Star, Leadership in Energy and Environmental Design (LEED), and Cool Roof Rating Council (CRRC) approved methods for determining radiative properties.

The solar reflectance index (SRI) was calculated in compliance with ASTM E1980-11: *Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces*.

Sampling: The following materials were received by PRI.

<u>Product</u>	<u>Source</u>	<u>Date</u>	<u>Sampling</u>
Calacata	Tampa, FL	Sep. 13, 2021	Hardscape.com

2275T0003.12

The test results, opinions, or interpretations are based on the material supplied by the client. This report is for the exclusive use of stated client. No reproduction or facsimile in any form can be made without the client's permission. This report shall not be reproduced except in full without the written approval of this laboratory. PRI Construction Materials Technologies LLC assumes no responsibility nor makes a performance or warranty statement for this material or products and processes containing this material in connection with this report.

Results: All measurements were recorded at 73.4±1.8°F & 50±5%RH


ASTM E 1980

Product	Solar Reflectance		Thermal Emittance		SRI		
	ASTM C1549 ¹		ASTM C1371 ²		ASTM E1980 ³		
	Avg.	Std.Dev.	Avg.	Std.Dev.	Low-Wind	Med-Wind	High-Wind
Calacata - 24" x 24" x 3/4"	0.580	0.020	0.90	0.00	69	69	69

- Note(s):
- 1- Reflectance measurements were conducted using a Devices and Services SSR-ER Version 6.4 Reflectometer operated in v5 emulation mode and calibrated with Devices and Services Reference Tile # D-18.
 - 2- Emittance measurements were conducted using a Devices and Services Emissometer Model AE calibrated with Devices and Services Reference Standards: High Emittance: 0.86 and Low Emittance: 0.06. Thermal emittance measurement for sample was modified in accordance with Devices and Services Company's Tech Note 04-1.
 - 3- SRI calculations per ASTM E 1980 Approach II utilize the following assumptions: Low-Wind $h_c = 5 \text{ W/m}^2\cdot\text{K}$, Medium-Wind $h_c = 12 \text{ W/m}^2\cdot\text{K}$, and High-Wind $h_c = 30 \text{ W/m}^2\cdot\text{K}$.

Statement of Attestation: The Solar Reflectance Index of these samples was calculated in accordance with **ASTM E 1980: Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces**. The laboratory test results presented in this report are representative of the materials supplied.

Signed:



Brent Barbeau
 Manager

Date:

Sep. 22, 2021

Report Issue History:

Issue #	Date	Pages	Revision Description (if applicable)
Original	Sep. 22, 2021	2	NA

END OF REPORT

2275T0003.12

The test results, opinions, or interpretations are based on the material supplied by the client. This report is for the exclusive use of stated client. No reproduction or facsimile in any form can be made without the client's permission. This report shall not be reproduced except in full without the written approval of this laboratory. PRI Construction Materials Technologies LLC assumes no responsibility nor makes a performance or warranty statement for this material or products and processes containing this material in connection with this report.